

LOVE what you **PRESS!** 

PoliMelt

PM-700

Polimelt is used to bond foils to garments.

Application Instructions

Cotton, Uncoated Polyester, Cotton/Polyester, Polyester/Acrylic



45° Blade with very low pressure



Cut this material in mirror image



315°F - 330°F



Medium even pressure



15 - 20 seconds



Peel warm then add your foil according to its instructions



Wash warm, tumble dry normal. Suitable for dry-cleaning.

No nylon, dazzle cloth, or shiny polyester.

***For Dazzle Cloth, Shiny Polyester, and Moisture-wicking fabrics:**
 Damp a cloth with rubbing alcohol (isopropyl alcohol), then gently apply it to the area on the garment you want to apply your design. Allow it to dry and apply your material. This will allow better adhesion to the garment.

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

LOVE what you **PRESS!** 

PoliMelt

PM-700

Polimelt is used to bond foils to garments.

Application Instructions

Cotton, Uncoated Polyester, Cotton/Polyester, Polyester/Acrylic



45° Blade with very low pressure



Cut this material in mirror image



315°F - 330°F



Medium even pressure



15 - 20 seconds



Peel warm then add your foil according to its instructions



Wash warm, tumble dry normal. Suitable for dry-cleaning.

No nylon, dazzle cloth, or shiny polyester.

***For Dazzle Cloth, Shiny Polyester, and Moisture-wicking fabrics:**
 Damp a cloth with rubbing alcohol (isopropyl alcohol), then gently apply it to the area on the garment you want to apply your design. Allow it to dry and apply your material. This will allow better adhesion to the garment.

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.