

Specialty Materials™

THE BEST GARMENT DECORATION PRODUCTS



LOVE what you PRESS!



Digital Decoration Systems®

ColorPrint™ Solvent/Ecosol

ThermoBANNERPrintable™

White TBP-2060

A white PVC media with a semi-matte finish for use on Solvent/Eco-Solvent printers for heat transfer applications. Pressure sensitive and transparent polyester carrier allows for easy weeding. High printing quality with bright colors.

Applications

Textile awnings and other heat sensitive fabrics



45° Blade



Print and cut this material "right-reading"



Use TM-850 to transfer the image to the garment.



210°F



Very little pressure required. Use hand iron or standard heat press.



20 seconds



PEEL Peel cold



Wash inside out, cold water, tumble dry low

No nylon. This is a PVC product, which emits hazardous fumes when cut with a laser machine!

Roll Storage: Upright, one year in a dry room, 60-80°F, protected from sunlight.

Please make sure this material is free of dust and debris before printing by wiping the material with a dry cloth.

Please make sure this material is free of dust and debris before printing by wiping the material with a dry cloth.

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

Copyright © 2016, Specialty Materials & Digital Decoration, LLC. All rights reserved. 2929 W. 21st Street, Tulsa, OK 74107



LOVE what you PRESS!

BASIC INSTRUCTIONS FOR PRINTING PROFILE SETUP

The following settings are to be used when no profile is available. Most self-adhesive gloss vinyl profiles work well with our printable media after a slight lowering of the ink limits.

To avoid over-saturation, it is important to remember to slow the printing process by using high resolution and high pass count settings to allow the ink to absorb without beading or bleeding.

When cutting printable media, it is important to use a new or sharp blade and slow the speed of the contour to 10cm/sec or less. Always perform test cuts to ensure proper depth before sending the final job.

Mimaki JV3 (SS2 Inks)

Profile: Use Gloss Vinyl Profile
Resolution: 720 x 1440 or 1440 x 1440
Pass count: 16 or 32
Direction: Uni
Heat: Pre- 35 deg C (95 deg F)
Print- 30 deg C (86 deg F)
Vacuum: High
GCR Option: Medium
Total Ink Limit: 220%
Black Ink Start: 0%
Black Ink Limit: 85%
Multi Ink Limits: M+Y = 82%
C +Y = 80%
C +M = 80%
C+Y+ M= 78%

Roland VersaCamm (Eco Max)

Profile: Use Gloss Vinyl Profile or
TTRH with Color Management
set to max impact
Print Quality: High Quality
Resolution: 1440 x 720dpi
Mode: CMYK(v) W+PASS
Halftone: Dither
Interpolation: Nearest Neighbor
Direction: Uni-direction
Pass Count: 18
Scan Speed: 750
Heat: Print - 95°F, Dryer - OFF
Vacuum: Strong
GCR Option: Medium
Total Ink Limit: 190%
Black Ink Start: 0%
Black Ink Limit: 75%
Multi Ink Limits: M+Y = 85%
C +Y = 78%
C +M = 93%
C+Y+ M= 85%

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.