

Specialty Materials™



THE BEST GARMENT DECORATION PRODUCTS

Reflective *Printable*™

Digital Media for Textile Transfers
Designed for Solvent/Eco-Solvent Inks

Silver RP-MSSIL

Highly reflective polyurethane materials designed for printing with Solvent/Eco-Solvent printers. It is thin and easy to weed.

Acceptable Fabrics

Cotton, Uncoated Polyester, Acrylic, and Similar Fabrics
Excluding Nylon

Sizing Available

Available Widths (in.): 20" only
Available Lengths (ft.): 15', 30', 45', 60', 75', 90', 162' rolls

Thickness

5.8 mils/145 microns

Special Precautions

Please note: Printed colors may look subdued,
due to the reflectivity of the material.



60° Blade
Recommended



Print and cut
this material
"right reading"



Use TM-854 or
KTM-500 to transfer
the image to the
garment.



320°F



Medium, even
pressure



15 Seconds



Peel cold



Wash inside out,
gentle cycle, warm water,
tumble dry low. Not
suitable for dry-cleaning.

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer. Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics.


Copyright © 2018, Specialty Materials & Digital Decoration, LLC. All rights reserved.

Specialty Materials™



THE BEST GARMENT DECORATION PRODUCTS

LOVE what you PRESS!



BASIC INSTRUCTIONS FOR PRINTING PROFILE SETUP

The following settings are to be used when no profile is available. Most self-adhesive gloss vinyl profiles work well with our printable media after a slight lowering of the ink limits.

To avoid over-saturation, it is important to remember to slow the printing process by using high resolution and high pass count settings to allow the ink to absorb without beading or bleeding.

When cutting printable media, it is important to use a new or sharp blade and slow the speed of the contour to 10cm/sec or less. Always perform test cuts to ensure proper depth before sending the final job.

Mimaki JV3 (SS2 Inks)

Profile: Use Gloss Vinyl Profile
Resolution: 720 x 1440 or 1440 x 1440
Pass count: 16 or 32
Direction: Uni
Heat: Pre- 35 deg C (95 deg F)
Print- 30 deg C (86 deg F)
Vacuum: High
GCR Option: Medium
Total Ink Limit: 220%
Black Ink Start: 0%
Black Ink Limit: 85%
Multi Ink Limits: M+Y = 82%
C +Y = 80%
C +M = 80%
C+Y+ M= 78%

Roland VersaCamm (Eco Max)

Profile: Use Gloss Vinyl Profile or
TTRH with Color Management
set to max impact
Print Quality: High Quality
Resolution: 1440 x 720dpi
Mode: CMYK(v) W+PASS
Halftone: Dither
Interpolation: Nearest Neighbor
Direction: Uni-direction
Pass Count: 18
Scan Speed: 750
Heat: Print - 95°F, Dryer - OFF
Vacuum: Strong
GCR Option: Medium
Total Ink Limit: 190%
Black Ink Start: 0%
Black Ink Limit: 75%
Multi Ink Limits: M+Y = 85%
C +Y = 78%
C +M = 93%
C+Y+ M= 85%

Technical Support: Toll Free: 877-437-8556 | SpecialtyMaterials.com

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer. Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics.

Copyright © 2018, Specialty Materials & Digital Decoration, LLC. All rights reserved.